


Intended use

High solid 2K high-build polyurethane acrylic coating with active corrosion protection in HS quality with high vertical stability up to 250 µm dry film thickness. Suitable for industrial, high-build and top-quality coatings of machines, construction components, constructions and construction machinery. For interior and exterior use. Direct adhesion on steel and zinc substrates.

This product complies with the requirements for fire behaviour of materials and components according to EN 45545-2:2013 + A1:2015.

Processing instructions**Mixing ratio****hardener****by weight (lacquer : hardener)****by volume (lacquer : hardener)**

PU 914-XX

6 : 1

4 : 1

PU 916-XX

8 : 1

6 : 1

**Hardener**

Mipa PU 914-10, PU 914-25, PU 914-40

Mipa PU 916-10, PU 916-25

**Pot life**

with hardener -10 approx. 1 h at 20 °C

with hardener -40 approx. 5 h at 20 °C

**Thinner**

Mipa 2K-Verdünnung V 10, V 25, V 40

**Processing viscosity**

Ready for use after adding hardener, if necessary thin with Mipa 2K-Verdünnung.

gravity spray gun**Airmix/Airless**

thixotropic

thixotropic

**Application mode****application mode****hardener****pressure
(bar)****nozzle
(mm)****spray
passes****dilution**gravity spray gun/
HVLP

–

2,0 - 2,2

1,5 - 2,5

2

0 %

Airmix / Airless
compound pressure

–

1,0 - 2,0
100 - 120

0,23 - 0,33

1

0 %

**Drying time****hardener****object
temperature****dust dry****set to
touch****ready for
assembly****sandable****recoatable**

–

20 °C

20 - 25 min

1 - 2 h

24 h

–

–

–

60 °C

–

–

30 min

–

–

Fully cured after 5 - 6 days (20 °C).

Note**Characteristics:**

binder base:	polyurethane acrylic system
solids content (% by weight):	~ 72
solids content (% by volume):	~ 54
delivery viscosity DIN 53211 4 mm (in s):	thixotropic
density DIN EN ISO 2811 (kg/l):	~ 1,4
gloss level ISO 2813 at 60° (GU):	70 - 80 satin gloss

Properties:

Electrostatic application possible
Active corrosion protection (zinc phosphate)
Highly UV- and weather-resistant
Very good water resistance, solvent resistant
Highly resistant to fuels and oils
High vertical stability (up to approx. 250 µm dry film thickness)
Heat resistance: - Short-term heat exposure: 180 °C
- Permanent heat exposure: 150 °C
Adheres on steel
Adhesion on zinc-coated substrates: Gt 0 - 1

Theoretical spreading rate:

~ 43,3 m²/kg, 8:1 by weight with PU 916-25, for 10 µm dry film thickness.
~ 55,4 m²/l, 8:1 by weight with PU 916-25, for 10 µm dry film thickness.
~ 41,6 m²/kg, 6:1 by weight with PU 914-25, for 10 µm dry film thickness.
~ 51,9 m²/l, 6:1 by weight with PU 914-25, for 10 µm dry film thickness.

Storage:

For at least 3 years in the unopened original container. Optimum storage conditions between + 5 °C and + 25 °C, avoid direct sunlight. Other storage conditions may lead to undesirable properties of the material.

VOC:

< 430 g/l.*

Processing conditions:

From + 10 °C and up to 80 % relative humidity. Ensure adequate air ventilation.

Substrate preparation:

Remove oil, grease, rust, mill scale, rolling skins, as well as other substances impairing the function of the coating!

Attention: A direct adhesion cannot be taken as granted due to most different kinds of metals, alloys, metallic and conversion coatings and so on. The adhesion must therefore be tested on the original substrate.

Steel:

- Blast to cleaning degree Sa 2½, remove blast residues and overcoat promptly.
- De-rust with hand and power tools to degree of cleanliness St 3.
- Degrease with Mipa WBS Reiniger or Mipa Silikonentferner.

Zinc-coated substrates:

- Clean the surface with the ammonia solution Mipa Zinkreiniger.
- Sweep blast.

Aluminium:

- Degrease with Mipa 2K-Verdünnung, sand thoroughly with sandpaper P 360/400 and clean subsequently with Mipa Silikonentferner.

Proposed coating structure: Single coat system
Steel, zincd substrates:
PU 266-70 with 80 - 150 µm dry film thickness.

2-coat system
Steel, zincd substrates, aluminium:
Priming coat: **EP 100-20 with 50 - 70 µm dry film thickness or with 25 - 30 µm dry film thickness on aluminium.
Finishing coat: PU 266-70 with 80 - 150 µm dry film thickness.

3-coat system
Steel, zincd substrates:
Priming coat: **EP 100-20 with 50 - 70 µm dry film thickness.
Intermediate coat: EP 564-20 with 80 - 150 µm dry film thickness.
Finishing coat: PU 266-70 with 80 - 150 µm dry film thickness.

Special notes:

*This product contains the following maximum VOC-values:
- Applied by spraying with hardener PU 916-XX: < 440 g/l of VOC.
- Applied by spraying with hardener PU 914-XX: < 460 g/l of VOC.

**Further Mipa primers are available. Please contact your technical adviser or our application technicians.

For professional use only.

The details of the paragraphs - Proposed coating structure, Characteristics, Theoretical spreading rate, VOC - refer to the colour shade RAL 7035. For other colour shades, these may deviate.

Especially UV-resistant pigmentations (e.g. pastel shades for facades) are available on demand.

Check colour shade prior to application.

In case of application by means of an Airmix/Airless device, it is recommended testing beforehand the equipment for its suitability. If micro foam or blistering emerge during the application with an Airmix/Airless device, it is recommended adding more thinner or using the additives 2K-Systemzusatz PUA and PUS. Furthermore, the film thickness should be kept as low as possible.

If required we also offer hardeners and cleaning agents that are suitable for 2-component mixing and dosing units. Please contact your technical adviser or our application technicians.

Depending on the hardener in use and on the processing condition, the gloss level may prove to be higher or lower. The mentioned data refer to the hardener of series: PU 914-XX.

Cleaning of tools:

Clean tools immediately after use with Mipa Nitroverdünnung.