








Intended use

Thixotropic high-build monolayer paint to coat constructions (halls, pipes, doors, wall and ceiling panels, roofs, recipients, container, vehicle constructions) made of steel, zincd steel, aluminium and PVC. Suitable for brush, roller and spray application. For interior and exterior use. This paint can also be applied to mineral substrates (concrete, screed, and so on).

Processing instructions

	Mixing ratio hardener	by weight (lacquer : hardener)		by volume (lacquer : hardener)				
	--	--		--				
	Hardener	--						
	Pot life	--						
	Thinner	Mipa UN-Verdünnung Mipa Verdünnung UN 21						
	Processing viscosity	Ready for use, if necessary thin with ipa UN-Verdünnung or Verdünnung UN 21.						
	gravity spray gun	Airmix/Airless						
	--	--						
	Application mode	application mode	hardener	pressure (bar)	nozzle (mm)	spray passes	dilution	
	brush, roller	--	--	--	--	0 %		
	Drying time	hardener	object temperature	dust dry	set to touch	ready for assembly	sandable	recoatable
	--	20 °C	25 - 30 min	4 - 5 h	8 - 10 h	--	--	
	--	60 °C	--	30 min	30 min	--	--	

Fully cured after 8 - 10 days (at 20 °C).

Note

Characteristics:	binder base:	vinyl copolymer
	solids content (% by weight):	~ 69
	solids content (% by volume):	~ 47
	delivery viscosity DIN 53211 4 mm (in s):	thixotropic
	density DIN EN ISO 2811 (kg/l):	~ 1,5
	gloss level ISO 2813 at 60° (GU):	20 - 30 satin matt

Properties:	good edge coverage electrostatic application possible very good water resistance heat resistance: - short-term heat exposure: 90 °C - permanent heat exposure: 70 °C adhesion to steel, zincd substrates, aluminium, hard PVC and concrete
Theoretical spreading rate:	~ 34,1 m ² /kg for 10 µm dry film thickness ~ 47,2 m ² /l for 10 µm dry film thickness
Storage:	For at least 3 years in the unopened original container. Optimum storage conditions between + 5 °C and + 25 °C, avoid direct sunlight. Other storage conditions may lead to undesirable properties of the material.
VOC:	< 500 g/l.*
Processing conditions:	From + 10 °C and up to 80 % relative humidity. Ensure adequate air ventilation.
Substrate preparation:	Remove oil, grease, rust, mill scale, rolling skins, as well as other substances impairing the function of the coating! Attention: A direct adhesion cannot be taken as granted due to most different kinds of metals, alloys, metallic and conversion coatings and so on. The adhesion must therefore be tested on the original metal substrate. steel: - blast to cleaning degree Sa 2½, remove blast residues and overcoat promptly - de-rust with hand and power tools to degree of cleanliness St 3 - degrease with Mipa WBS Reiniger or Mipa Silikonentferner zincd substrates: - clean the surface with the ammonia solution Mipa Zinkreiniger - sweep blast aluminium: - degrease with Mipa 2K-Verdünnung, sand thoroughly with sandpaper P 360/400 and clean subsequently with Mipa Silikonentferner hard PVC: - clean (remove completely any mould release agents), degrease with Mipa Kunststoffreiniger, sand slightly and degrease again with Mipa Kunststoffreiniger mineral substrates (concrete, plaster): - mineral substrates (set, dimensionally stable, rough and solid) must be free from friable parts and other substances that may affect the adhesion (e.g. rubber marks, greases, oils, rust, dust and similar)

Proposed coating structure: single coat system
steel, zincd substrates, aluminium:
VC 250-30 with 200 - 240 µm dry film thickness

PVC:
VC 250-30 with 80 - 120 µm dry film thickness

2-coat system
steel, zincd substrates:
priming coat: **VB 100-20 min 20 - 30 µm or EP 100-20 with 50 - 70 µm dry film thickness
finishing coat: VC 250-30 with 200 - 240 µm dry film thickness

aluminium:
priming coat: **VB 100-20 min 20 - 30 µm or EP 100-20 with 25 - 30 µm dry film thickness
finishing coat: VC 250-30 with 200 - 240 µm dry film thickness

concrete/ mineral substrates:
priming coat: Tiefgrund LH (exterior use) or Tiefgrund LF (interior use)
finishing coat: VC 250-30 with 80 - 120 µm dry film thickness

Special notes:

*This product has the following maximum VOC-values:
- Applied by brush/ roller: < 500 g/l of VOC.

**Further Mipa primers are available. Please contact your technical adviser or our application technicians.

For professional use only.

The details of the paragraphs - Proposed coating structure, Characteristics, Theoretical spreading rate, VOC - refer to the colour shade RAL 7035. For other colour shades, these may deviate.

Due to the system, strong exposure to UV and weathering may cause chalking. In addition, the thermoplastic behaviour of the coating must be observed at higher temperatures.

Check the colour prior to application.

Cleaning of tools:

Clean tools immediately after use with Mipa Nitroverdünnung.