

# Mipa Kontroll-Spray

Item no. 21210 0000

Technical data sheet

**mipa**

Professional Coating Systems

page 1 / 2

## Intended use

Mipa Kontroll-Spray schwarz is a black guide coat that is used to make irregularities visible when sanding putty and filler surfaces. It reveals any imperfections in the surface, as it blackens the remaining slow spots during flattening that have been caused by irregularities or pitting. Once the entire guide coat has been removed, you can be assured that the remaining filler or putty surface is smooth, absolutely flat and free from imperfections.

## Processing instructions



### Substrates

Putty and filler surfaces

### Pre-treatment / cleansing

Pre-clean with Mipa Silikonentferner.

Please refer to the section "Substrate preparation" for detailed information.

### Characteristics

Fast drying

Effective product for detecting unevenness on putty and filler surfaces

Very easy to sand

## Colour / Gloss level

black / matt



### Preparation


Before use, shake can vigorously for 1 - 2 minutes!



### Application

Spray to test - Spray distance approx. 20 - 30 cm

Apply 1 thin, even, not opaque coat!



### Flash-off time

-




### After use

After use, turn can upside down and spray until the valve is clean, this prevents the valve from clogging up.

Version: en 0122

This technical data sheet is supplied for informational purposes only! According to our information, all data and recommendations correspond to the state of art and are based on years of experience in manufacturing our products. They do not exempt the user from his obligation to verify professionally, on his own responsibility, the suitability of our products to the intended purpose under prevailing conditions. Safety data sheets and warnings on packaging must be observed. We reserve the right to modify and to complete the information content at any time, without prior notice or obligation to update.

MIPA SE · Am Oberen Moos 1 · D-84051 Essenbach · Tel.: +49(0)87 03/922-0 · Fax: +49(0)87 03/922-100 · mipa@mipa-paints.com · www.mipa-paints.com



## Drying time at 20 °C

Sandable after approx. 5 - 10 min

## Processing conditions

From +10 °C and up to 80 % relative humidity. Ensure adequate air ventilation.

## Storage

Can be stored for 2 years in cool and dry places.

## VOC-regulation

EU limit value for the product (cat. B/e): 840 g/l  
This product contains max. 720 g/l of VOC.

## Safety information

See safety data sheet