

Product description

Operational Sector : Satin gloss, hard-wearing latex paint on dispersion base, for interior use, in living and work areas.
Designed specifically for rough-, relief- or print ingrain wallpaper to help the user achieve the best possible finish by accentuating the structure through a beautiful satin gloss effect. High recommended for surfaces submitted to severe working loads.

Features :

- Solvent-free, free of plasticizers
- Excellent opacity
- Neutral odour
- Not sensitive to domestic normal soiling and easy to clean
- S_d-value: class 1 (determined as per DIN EN ISO 7783-2)
- Degree of whiteness CIE: 82 luminance factor: 87.
- Good filling, suitable for ingrain wall paper and rough render
- White paint also suitable for exterior use
- free from substances causing magic dust
- with requirements of EN 71-3 (Migration of Certain Elements) and DIN 53 160-1/2 (colour fastness to saliva and sweat)

Characteristic values as per DIN EN 13300:

- Wet abrasion class 2
- Opacity grade 2, by a consumption of 7 m² / litre
- Gloss degree: satin gloss
- Max. grain size: fine (<100 µm)

By tinting a negligible deviation from the given values should be considered.

Content as per VdL Directive 01 : Acrylate dispersion, titan dioxide, calcium carbonate, water, additives, preservation agent.

Colour availability : White
Tinting by Mipa Pro Mix Decorative

Specification :

Spec. weight: approx. 1.30	g/cm ³	DIN 51 757
Viscosity: approx. 95	dPas	DIN 53 019
pH-value: 8.1		DIN 53 785

Storage : At least 2 years, if the tightly closed original packages are kept dry, protected against frost. Storage temperature: from +5°C till maximum +30°C.

VOC legislation : EU limiting value for the product (cat. A/a): 75 g/l (2007)/ 30 g/l (2010). This product contains 0 g/l VOC [0 lbs/gal]

Application

Processing conditions : From + 5 °C up to + 35 °C and max. 75% relative air humidity.
Avoid direct sunlight and strong wind.

Suitable substrates : Old and new plastering (mortar group P II, P III, P IV a,b,c), concrete, limestone, ingrain wallpapers, plaster plates, glass fabric, as well as sound and firm adhering old coats.

This technical data sheet is supplied for informational purposes only! According to our information, all data and recommendations correspond to the state of art and are based on years of experience in manufacturing our products. They do not exempt the user from his obligation to verify professionally, on his own responsibility, the suitability of our products to the intended purpose under prevailing conditions. Safety data sheets and warnings on packaging must be observed. We reserve the right to modify and to complete the information content at any time, without prior notice or obligation to update.

Substrate preparation :	The substrate has to be clean, dry, firm and sound. Remove damaged, not adhesive old layers of paint. Renewed plastering should be setted and completely dried. In case of powdering, porous surfaces a primer should be used (Mipa Tiefgrund LF). See VOB, part C, DIN 18363.
Application process :	Rolling, brushing or spraying (Airless): nozzle: 515 / 0.38 mm - 525 / 0.63 mm angle: 50 ° pressure: 120 bar The spraying parameters may be considered a guide in connection with choice of appliance and working method
Thinner :	Apply on contrasting, strongly absorbent surfaces a base coat thinned with 10 - 15% water and a top coat thinned with approx. 5 - 10% water.
Recommendation for end-use :	Stir well before use. Apply Mipa Latexfarbe seidenglänzend in smooth, level coats. Best results are obtained according to the precision of the application
Drying times :	At 20° C and 65% relative air humidity: dry to touch and recoatable: after approx. 8 hours. At lower temperatures the drying will take longer.
Spreading rate :	Depending on the substrate and the application: 7 m ² / litre per operation. The versatility of the operational sector (different structure and absorbence of the substrate) does not allow an exact figure. A test coat on the object is the best guarantee.

Special remarks

Mipa Latexfarbe seidenglänzend white (not coloured) may be also used as a particular finish for facades. Brilliant, intensive colours may have in special circumstances a lower hiding power. Practical experience demonstrates that in this case it is better to use a related pastel shade based on white colour. Eventually a second finishing coat would be necessary. Mix well and strain before use by Airless application. Do not inhale aerosols.

Adverse light conditions (glancing light):

Recommendation: Apply Mipa Ultra or Ultima on smooth surfaces that are exposed to adverse light conditions (glancing light). When coating sealants, such as acrylic sealant compounds, cracks may occur in the coating due to higher elasticity of these substrates. Furthermore, it may cause discoloration in the coating. Due to large number of different sealing systems on the market, we recommend carrying out your own tests to assess the adhesion and coating results in each single case. Repair works on surfaces are more or less visible which depends on the conditions of the object. This is unavoidable according to BFS-Merkblatt Nr. 25, Punkt 4.2.2.1, Abschnitt e).

Safety instructions

Mipa Latexfarbe seidenglänzend is slightly alkaline. Protect eyes and sensitive skin against colour. Wash away colour traces immediately with sufficient clear water. Consider general hygienic rules.

This technical data sheet is supplied for informational purposes only! According to our information, all data and recommendations correspond to the state of art and are based on years of experience in manufacturing our products. They do not exempt the user from his obligation to verify professionally, on his own responsibility, the suitability of our products to the intended purpose under prevailing conditions. Safety data sheets and warnings on packaging must be observed. We reserve the right to modify and to complete the information content at any time, without prior notice or obligation to update.

Cleaning of tools

Tools should be cleaned immediately after use with water.

This technical data sheet is supplied for informational purposes only! According to our information, all data and recommendations correspond to the state of art and are based on years of experience in manufacturing our products. They do not exempt the user from his obligation to verify professionally, on his own responsibility, the suitability of our products to the intended purpose under prevailing conditions. Safety data sheets and warnings on packaging must be observed. We reserve the right to modify and to complete the information content at any time, without prior notice or obligation to update.