

Product description

Operational Sector :	Pigmentated special primery coat developed specifically as non-slip, excellent adhesion promoter for plastering or dispersion top coats. For interior and exterior use.	
Features :	<ul style="list-style-type: none"> - weather resistant corresponding to VOB Teil C, DIN 18 363 - excellent adhesion to slippery and critical substrates - specifically developed as priming coat for roughcasts - high diffusion - water thinnable and odourless - resistant to alkali 	
Content as per VdL Richtlinie 01 :	Acrylate dispersion, titan dioxide, marble, water, calcium carbonate, additives, preservative	
Binder base :	synthetic dispersion according to DIN 55 947	
Pigmentation base :	titan dioxide	
Colour availability :	white	
Specification :	Gloss: mat	DIN 67 530
	Spec. weight: 1.65 g/cm ³	DIN 51 757
	Viscosity: 100 dPas	DIN 53 019
	pH-value: 8.5	DIN 53 785
Storage :	At least 2 years, if the tightly closed original packages are kept dry, protected against frost. Storage temperature: from +5°C till maximum +30°C.	
VOC-regulation:	EU limiting value for the product (cat. A/h): 50 g/l (2007)/ 30 g/l (2010) This product contains 0 g/l VOC [0 lbs/gal]	

Application

Processing conditions :	Do not apply below + 5° C and more than +35° C temperature of the object or the environment. Avoid direct sunlight and strong wind.
Suitable substrates :	Old and new plastering, fibred cement boards (please see BFS – Merkblatt Nr. 14), concrete, limestone as well as sound, adhesive old layers of paint on dispersion or synthetic base.
Substrate preparation :	The substrate has to be clean, dry, firm and sound. Remove damaged, not adhesive old layers of paint and distemper. Renewed roughcast should be setted and completely dried.

This technical data sheet is supplied for informational purposes only! According to our information, all data and recommendations correspond to the state of art and are based on years of experience in manufacturing our products. They do not exempt the user from his obligation to verify professionally, on his own responsibility, the suitability of our products to the intended purpose under prevailing conditions. Safety data sheets and warnings on packaging must be observed. We reserve the right to modify and to complete the information content at any time, without prior notice or obligation to update.

In case of powdering, porous surfaces a primer should be used (Mipa Tiefgrund LF or Mipa Tiefgrund LH).

Application process : Brushing and rolling.

Dilution : 10 - 20% with water.

Application : Stir well before use. Apply Mipa Putzgrund in smooth, level coats. Best results are obtained according to the precision of the application.

Drying times : At 20° C and 65% relative air humidity:
set to touch and recoatable : after approx. 8 hours.
At lower temperatures and higher air humidity, the drying will take longer.

Consumption : Depending on the absorbency of the substrate:
approx. 4m² / liter per operation. A test coat on the object would give you an exact figure.

Safety instructions

Mipa Putzgrund is slightly alkaline. Protect eyes and sensitive skin against colour. Wash away colour traces immediately with sufficient clear water. Consider general hygienic rules.

Cleaning of tools

Tools should be cleaned immediately after use with water.

This technical data sheet is supplied for informational purposes only! According to our information, all data and recommendations correspond to the state of art and are based on years of experience in manufacturing our products. They do not exempt the user from his obligation to verify professionally, on his own responsibility, the suitability of our products to the intended purpose under prevailing conditions. Safety data sheets and warnings on packaging must be observed. We reserve the right to modify and to complete the information content at any time, without prior notice or obligation to update.