

Description

Intended use:	Miparit is a ready-to-use putty for sealing fissures in masonry and plastering as well as for levelling out asperities. For interior and exterior use. Miparit is also suitable for cosmetic repairs on concrete surfaces.										
Properties:	<ul style="list-style-type: none">- impermeable to water up to 10 bar- weather-resistant and non-ageing- elastic-plastic- recoatable- skin time after 15 - 20 minutes at 23°C										
Content :	Based on acrylate dispersion										
Treated product:	Contains a biocidal product. Contains a mixture of: 5-Chloro-2-methylisothiazol-3(2H)-one [EC no. 247-500-7] and 2-methylisothiazol-3(2H)-one [EC no. 220-239-6] (3:1). Can cause allergic reactions.										
Colour:	Pearl white										
Specification:	<table><tr><td>viscosity:</td><td>pasty, vertical stability</td></tr><tr><td>specific weight:</td><td>approx. 1,56 g/cm³ DIN 51 757</td></tr><tr><td>shore A hardness:</td><td>approx. 25 DIN 53 505</td></tr><tr><td>movement absorption:</td><td>approx. 5%</td></tr><tr><td>temperature resistance:</td><td>- 20° C up to + 80° C</td></tr></table>	viscosity:	pasty, vertical stability	specific weight:	approx. 1,56 g/cm ³ DIN 51 757	shore A hardness:	approx. 25 DIN 53 505	movement absorption:	approx. 5%	temperature resistance:	- 20° C up to + 80° C
viscosity:	pasty, vertical stability										
specific weight:	approx. 1,56 g/cm ³ DIN 51 757										
shore A hardness:	approx. 25 DIN 53 505										
movement absorption:	approx. 5%										
temperature resistance:	- 20° C up to + 80° C										
Storage :	At least 2 years in unopened original containers, if stored in dry and frost-free places at a temperature between +5°C and max. +30°C.										

Application

Processing conditions:	Do not apply at substrate and ambient temperature below 5 °C. Protect the coat against rain until a surface skin has formed.
Suitable substrates:	Mineral substrates (concrete, masonry, and so on).
Substrate preparation:	The substrate must be clean, solid and dry. Remove old, flaking material by brushing. Scratch fissures out, and clean both sides of the cracks. Damp down the gap with water.

This technical data sheet is supplied for informational purposes only! According to our information, all data and recommendations correspond to the state of art and are based on years of experience in manufacturing our products. They do not exempt the user from his obligation to verify professionally, on his own responsibility, the suitability of our products to the intended purpose under prevailing conditions. Safety data sheets and warnings on packaging must be observed. We reserve the right to modify and to complete the information content at any time, without prior notice or obligation to update.

Application : Apply Miparit evenly by means of manual or pneumatic cartridge gun. Skim the surface using for example a spatula or similar before skin formation. Once cured through, Miparit is recoatable with dispersion paints.

Drying time : Dry to touch after approx. 2 hours at 20 °C and 65 % relative humidity.

Notes

Ensure that the filler won't get in contact with rain or any water. Even if joint sealers are recoatable, it is recommended not to recoat because of the risk of fissures due to movement.

Safety advices

Consider general hygienic rules.

Cleaning of tools

Clean tools with water immediately after use or in case of prolonged interruption of work.

This technical data sheet is supplied for informational purposes only! According to our information, all data and recommendations correspond to the state of art and are based on years of experience in manufacturing our products. They do not exempt the user from his obligation to verify professionally, on his own responsibility, the suitability of our products to the intended purpose under prevailing conditions. Safety data sheets and warnings on packaging must be observed. We reserve the right to modify and to complete the information content at any time, without prior notice or obligation to update.